



High alumina brick LZ-80

Physical and chemical index

Item:	LZ-80	
Al ₂ O ₃ %	≥80	
Apparent porosity %	≤22	
Cold crushing strength Mpa	≥55	
Refractoriness ℃	≥1790	
Refractoriness under loadin 0.2MPa	≥1530	
Permanent linear change	1500 ℃×2h	-0.4~0.1
	1450 ℃×2h	-