



ZHENGZHOU SUNRISE REFRACTORY CO., LTD

Sunrise REF. 7001 Common Zircon Brick ZS-64

Common Zircon Brick

Brand: Sunrise

Physical and chemical index

Item	ZS-64
ZrO ₂ (%)	≥64
SiO ₂ (%)	≤34
Fe ₂ O ₃ (%)	≤0.5
Apparent Porosity (%)	≤20
Bulk Density (g/cm ³)	≥3.6
Cold Crushing Strength (Mpa)	≥100
0.2Mpa Refractoriness Under Load T _{0.6} °C	≥1630
Pyrometric Cone Equivalent S.C. SK	40
Reversible Thermal Expansion 1000°C %	0.5