



Dense Zircon Block

Brand: Sunrise

Physical and chemical index

Item	ZS-65
ZrO ₂ (%)	≥65
SiO ₂ (%)	≤33
Fe ₂ O ₃ (%)	≤0.5
Apparent Porosity (%)	≤18
Bulk Density (g/cm ³)	≥3.65
Cold Crushing Strength (Mpa)	≥100
0.2Mpa Refractoriness Under Load T _{0.6} °C	≥1650
Pyrometric Cone Equivalent S.C. SK	40
Reversible Thermal Expansion 1000°C %	0.5