



High Alumina Insulation Brick

Brand: Sunrise

Physical and chemical index

Brand	LG-0.8
Inedx	
Al ₂ O ₃ ,% \geq	48
Fe ₂ O ₃ ,% \leq	2.0
Bulk Density (g/cm ³) \leq	0.8
Cold Crushing Strength Mpa \geq	2.94
Thermal Conductivity (350°C)W/m.K \leq	0.35
Temp reheating shrinkage less than 2.0% °C	1400