



## High Alumina Insulation Brick

Brand: Sunrise

Physical and chemical index

Inedx	Brand	LG-0.9
Al <sub>2</sub> O <sub>3</sub> ,%	≥	48
Fe <sub>2</sub> O <sub>3</sub> ,%	≤	2.0
Bulk Density (g/cm <sup>3</sup> )	≤	0.9
Cold Crushing Strength Mpa	≥	3.43
Thermal Conductivity (350°C)W/m.K	≤	0.45
Temp reheating shrinkage less than 2.0% °C		1400