



High Alumina Insulation Brick

Brand: Sunrise

Physical and chemical index

Inedx	Brand	LG-1.2
Al ₂ O ₃ ,%	≥	48
Fe ₂ O ₃ ,%	≤	2.0
Bulk Density (g/cm ³)	≤	1.2
Cold Crushing Strength Mpa	≥	5
Thermal Conductivity (350°C)W/m.K	≤	0.55
Temp reheating shrinkage less than 2.0% °C		1400