



HIGH ALUMINA BRICK LZ-85

Physical and chemical index

Item:		LZ-85
Al ₂ O ₃ %		≥85
Apparent porosity %		≤23
Cold crushing strength Mpa		≥55
Refractoriness °c		≥1790
Refractoriness under loadin 0.2MPa		≥1550
Permanent linear change	1500 °c ×2h	-0.4~0.1
	1450 °c ×2h	-