



## HIGH ALUMINA CASTABLE JGL-70

Physical and chemical index

Item	JGL-70
Al <sub>2</sub> O <sub>3</sub> , %	≥70
Cold Crushing Strength Mpa, after drying at (110°C ±5°C)	≥35
MOR, Mpa (after drying at (110°C ±5°C)	≥5
Linear Change after heating less than +1% test temperature, °C (heat preservation for 3hrs)	1450
Refractoriness, °C	≥1720